

To calculate the crimp in yarn affected by knitting or weaving, to determine actual yarn usage. Threads are removed from a strip of fabrics of known length, straightened by a tension, then measured in the straightened state. Two tension ranges available (0-35 g and 0-175 g) and test length is 120 cm (48 inches).

## SIZE

WEIGHT	4 kg / 9 lbs
DIMENSIONS	1500 mm (w) $\times$ 80 mm (d) $\times$ 40 mm (h) / 60 in (w) $\times$ 3.5 in (d) $\times$ 1.5 in (h)

## ORDERING INFORMATION

105676	Crimp Tester	•		
STANDARDS:				
ISO 7211	BS 2863	BS 2865	BS 2866	
Woolmark TM 169				